





# 8745 Harness Splice Tape

High quality Soft PVC Film, coated with a strong rubber based adhesive, hand applicable, 105°C.

#### **FEATURES:**

- Rubber adhesive
- PVC carrier

#### **BENEFITS:**

- Flame resistant
- Controlled, even unwind
- Superior adhesion
- Excellent conformability
- Application by dispenser or hand
- Resistant to engine compartment fluids
- Meet RoHS & REACH



# STANDARD SIZES:

Length: 50m, 100mm

Width: 40mm

Core ID: 38mm, 76.2mm

## **COLORS:**

Blue

Other sizes and colors are available on request.





#### 8745

| Properties          | Value                 | Unit | Test Method        |
|---------------------|-----------------------|------|--------------------|
| Total thickness     | 0.190±0.02            | mm   | EN 1942            |
| Tensile strength    | >32                   | N/cm | ISO 29864          |
| Elongation at break | >220                  | %    | ISO 29864          |
| Adhesion strength   |                       |      | ISO 29862          |
| — to steel          | >1.7                  | N/cm |                    |
| — to backing        | >1.6                  | N/cm |                    |
| Unwind force        | 2.5~6.0               | N/cm | EN 1944            |
| Flammability        | B(self-extinguishing) |      | GMW 16740 / LV 312 |
| Breakdown voltage   | 8                     | kV   | ASTM D1000         |
| Temperature rating  | B:-25~105             | °C   | GMW 16740 / LV 312 |

Note: The listed values are required only and not intended to serve as product specifications

## **RECOMMENDED USES:**

Use as permanent splice covering on wiring harnesses for passenger vehicles, trucks, construction equipment, farm implements, aircraft, aerospace and electronic assemblies. Preferred when requirements include a need for long term reliability under varying and extreme environmental conditions.

## STORAGE AND SHELF LIFE

The shelf life of the product is five years when stored at 20-30°C, max 65% relative humidity and out of direct sunlight, in original packaging.

All technical information and data mentioned are provided to the best of our knowledge on the basis of our lab tests believed to be reliable. They shall be considered as typical values and are not appropriate for a specification. Therefore, all statements, technical information and recommendations concerning products sold or samples provided by Avery Dennison Yongle do not constitute a guarantee or warranty. All products are sold with the understanding that the user has independently determined the suitability of such products for its application purposes.

©2021 Avery Dennison Corporation. All rights reserved. Avery Dennison Yongle is a trademark of Avery Dennison Corporation. Plyon and all other Avery Dennison brands, product names or service programs are trademarks of Avery Dennison Corporation.



